

ROOFTEX FV 100

ROOFTEX FV 100 is a fibre glass felt created with longitudinally reinforced threads.

ADVANTAGES

- Flame resistant
- High dimensional stability



APPLICATION

- ROOFTEX FV 100 is specifically recommended for use as a separating layer between the waterproofing membrane and the base support.

Bituminous Waterproofing Auxiliary

TEXSA SYSTEMS SLU reserves the right to modify the information contained herein without prior notice and declines all liability in cases of errors produced due to inappropriate use of the product. The values shown in the technical sheet are the mean values from tests in our lab.

PACKAGING AND STORAGE

| | ROOFTEX FV 100 |
|----------------------|----------------|
| g/m ² | 100 |
| Length (m) | 100 |
| Width (m) | 1.00 |
| m ² /roll | 100 |

Storage: The product should be kept in its original polyethylene wrapping until it is installed.

TECHNICAL PROPERTIES

| PROPERTIES | Unit | Test method | ROOFTEX FV 100 |
|-----------------------------|------------------|-----------------|----------------|
| Mass per unit area | g/m ² | UNE 104-281/6-2 | 100 |
| Lengthwise tensile strength | N/5cm | UNE 104-281/6-6 | 350 |
| Crosswise tensile strength | N/5cm | UNE 104-281/6-6 | 200 |
| Dimensional stability | % | UNE 104-281/6-7 | 0 |
| Thickness | mm | - | 0.5 |

Bituminous Waterproofing Auxiliary

TEXSA SYSTEMS SLU reserves the right to modify the information contained herein without prior notice and declines all liability in cases of errors produced due to inappropriate use of the product. The values shown in the technical sheet are the mean values from tests in our lab.