


VINITEX SA

Synthetic homogeneous PVC-P membrane, obtained by coextrusion.

ADVANTAGES

- Waterproof and resistant to UV rays
- Adaptable to structural movement
- High puncturing resistance
- Flexibility at low temperatures



APPLICATION

- Maximum flexibility for detailing, corners, parapets, etc.

Synthetic Waterproofing PVC

TEXSA SYSTEMS SLU reserves the right to modify the information contained herein without prior notice and declines all liability in cases of errors produced due to inappropriate use of the product. The values shown in the technical sheet are the mean values from tests in our lab.

PACKAGING AND STORAGE

	Vinitex SA 1.5
Length (m)	20
Width (m)	1.05
m ² /roll	21
N ^o roll/pallet	46
m ² /pallet	966
Colour (Surface / underside)	Light grey / Dark grey

Storage: Horizontal and parallel (never crossed). Supplied in roll son cardboard tubing. Store in the original packaging in a dry and cool place.

TECHNICAL PROPERTIES

PROPERTIES	Unit	Test method	Vinitex SA 1.5
Thickness	mm	EN 1849-2	1.5 ±5%
Mass per unit area	Kg/m ²	EN 1849-2	1,95 ±5%
Water tightness	-	EN 1928 (B)	Pass
Tensile strength	N/mm	EN 527-3	≥ 17,5
Elongation to Break	%	EN 527-3	≥ 300
Resistance to impact	mm	EN 12691 (A)	≥ 800
Static puncture resistance	N	EN 12236	≥1800
Tear resistance	N	EN 12310-2	≥ 80
Foldability at low temperatures	°C	EN 495-5	≤ - 30
Root resistance	-	EN 13948	Pass
Artificial aging due to prolonged exposure to UV radiation high temperatures and water	Visual (1000h)	EN 1297	No cracking
Water permeability after 6 hrs at 0.5Mpa		EN 1928 (B) EN 14150	Watertight

Synthetic Waterproofing PVC

TEXSA SYSTEMS SLU reserves the right to modify the information contained herein without prior notice and declines all liability in cases of errors produced due to inappropriate use of the product. The values shown in the technical sheet are the mean values from tests in our lab.